

### TECHNICAL DATA SHEET

#### PRODUCT DESCRIPTION:

Acryl-R<sup>®</sup> SM5514 is a self-leveling, low VOC, one component acrylic compound designed to seal mechanically fixed joints. After solvent release, this sealant exhibits a tough ductile mass that fulfills the sealant requirements of window, door, recreational vehicle, cargo trailer and manufactured home details.

#### ADVANTAGE:

- Excellent adhesion
- Outstanding UV resistance – non yellowing
- Easy to apply
- Fast skinning
- Cures to a ductile consistency
- Permanently flexible
- Paintable/ Mildew resistant
- Primerless adhesion to substrates, including anodized and mil finish aluminum, steel, galvanized steel, fiberglass, many plastics and rubber roofs.

#### TYPICAL USES:

- Narrow corner joints and screw heads.
- Waterproofing rivet seams and roof nails.
- Sealing gutters
- Sealing vehicle bodies, cab construction, underbody compartments and roofing.
- Sealing front and rear spoilers, auto trim, moldings, body seams and weld joints.
- Sealing corner moldings, fabricated roof-lap seams, bumper assemblies and body-to-cab joints in mini-motor homes.

#### APPLICATION LIMITATIONS:

Not recommended for use:

- On frost-bearing surfaces or when the temperature is below 40°F (4.6°C)
- On joints that will be subjected to continuous water immersion.
- Joints contaminated with silicone type cutting or fabricating oils.
- As a sealant on polycarbonate or acrylic surfaces when in tension.
- On polystyrene or foam insulation.
- Dynamic expansion joints.

#### TYPICAL PROPERTIES:

Property	Typical Value
Odor:	Sweet solvent odor before cure; None after cure
Percent Solids:	55 % Min.
VOC	<1 g/L, EPA Method 24
VOC	479.3 g/L, SCAQMD Method 24
Viscosity:	44,000 – 83,200 cps
Flash Point: (ASTM D56 – Tag Closed Cup)	63°F (17°C)
Elongation: (ASTM D412)	200% Min.
Hardness: (ASTM C661 – Shore A)	30 – 35 A
Peel Adhesion: (ASTM C794) (glass/aluminum)	12 pli (2.1 kN/m)
Sag: (ASTM D2202)	0.4" max.
Water Resistance: (AAMA 800)	Pass
Application Temperature Range:	55°F – 75°F (12.8°C – 23.4°C)
Service Temperature Range:	0°F – 180°F (-18°C – 82°C)
SM5514 has a shelf life of 18 months when stored in original closed containers between 50°F (10°C) and 80°F (26.67°C)	

#### SPECIFICATION COMPLIANCE:

AAMA 803.3  
(Narrow Joint Seam Sealers)

#### APPLICATION:

##### Surface Preparation

- Do not open until ready for use. Cut nozzle to desired bead size. Puncture seal inside spout.
- Exercise care during application and tooling to prevent air entrapment.
- Fill joints from the deepest point to prevent air entrapment.
- Tooling should be done in one continuous stroke.
- Excess sealant should be wiped from all surfaces while still uncured.
- If joint surfaces have been masked, remove masking tape immediately after tooling.
- Surfaces must be clean, dry and free of oil or grease.
- Mill finish aluminum may contain an invisible oil film or oxide. Clean with a good degreasing solvent such as xylene or toluene.

##### Joint Design

- Narrow joints (less than 3/32" [2.38mm] wide) should be sealed using a triangular or round bead which laps both adherends by 1/8" (3.17mm) minimum. Avoid applying sealant to one adherend edge before assembly as squeeze out will not provide sufficient

sealant in the joint. In all joints, sealant depth (thickness) would be at least 3/32" to 1/8".

- Joint width should not exceed 3/16" and sealant width should be sufficient to provide 1/8" minimum contact with each adherend.
- Use care in applying sealant on vertical surfaces as an excessive amount will cause flow from the joint and run down the surface.
- Do not over apply sealant.

#### Clean up

- Remove all excess sealant smears adjacent to the joint with xylene, toluene or methyl ethyl ketone\*.
- Tools and application equipment may also be cleaned with the same solvents.

\* The use of these solvents (or other solvents) be hazardous to your health. Use only in a well-ventilated area. KEEP AWAY FROM OPEN FLAME. Read all labeling before use. Follow solvent manufacturer's recommendations and instructions for safe handling.

#### PRECAUTIONS:

If this product is used in direct contact or in close proximity with any other sealant or elastomer, a compatibility test must be conducted by the purchaser or user prior to use. The suitability of this product, for each intended use, must be determined by the purchaser prior to acceptance.  
DO NOT HEAT PRODUCT.

#### PRETEST FOR ADHESION:

Pretest for adhesion is intended to eliminate potential field problems, by testing SM5514 with samples of substrates on which it will be applied. This testing will aid in determining the proper surface preparation method and effective cleaning techniques prior to application.

#### EXCLUSION OF WARRANTIES:

AS TO THE HEREIN DESCRIBED MATERIALS, ITW POLYMERS SEALANTS NORTH AMERICA, INC. MAKES NO WARRANTIES WHETHER EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SINCE THE USE OF THE HEREIN DESCRIBED MATERIALS INVOLVES MANY VARIABLES IN METHODS OF APPLICATION, HANDLING AND/OR USE, THE USER IN ACCEPTING AND USING THESE MATERIALS ASSUMES ALL RESPONSIBILITY FOR THE END RESULT. THE PURCHASE OF THIS ITW POLYMERS SEALANTS NORTH AMERICA, INC. PRODUCT IS SUBJECT TO THE TERMS AND CONDITIONS OF AN "AS IS" SALE, AND IF THE PRODUCT IS PROVED TO BE DEFECTIVE, THE EXCLUSIVE REMEDY, AT ITW POLYMERS SEALANTS NORTH AMERICA, INC.'S OPTION, SHALL BE TO REPLACE THE DEFECTIVE ITW POLYMERS SEALANTS NORTH AMERICA, INC. PRODUCT. ITW POLYMERS SEALANTS NORTH AMERICA, INC. SHALL NOT OTHERWISE BE LIABLE FOR LOSS OF DAMAGES, WHETHER DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL, REGARDLESS OF THE LEGAL THEORY ASSERTED, INCLUDING NEGLIGENCE, WARRANTY OR STRICT LIABILITY.

Complete technical information is available from  
ITW Polymers Sealants North America, Inc.